




COLORS FOR CONCRETE


ColorFlo® Granular • ColorFlo® Liquid

413 Colony Red	413 Clay (SRI 50)	750 Desert Tan (SRI 45)	750 Salmon (SRI 45)	306 Canvas (SRI 37)	306 Toffee (SRI 29)
413 Fox Red (SRI 37)	413 Terra Cotta (SRI 48)	750 Prairie Tan	750 Peach	306 Burlap (SRI 29)	306 Cinnamon
417 Rose	417 Brick Red (SRI 40)	775 Sand (SRI 46)	775 Cedar (SRI 45)	238 Thyme (SRI 44)	238 Doeskin (SRI 41)
417 Paver Red	417 Apple Red	775 Camel (SRI 45)	775 Sedona	238 Buttercup (SRI 44)	238 Marigold
489 Dusty Rose	489 Light Plum (SRI 24)	757 Buckwheat (SRI 44)	757 Pecan (SRI 41)	338 Earthen	338 Rawhide (SRI 25)
489 Redwood (SRI 22)	489 Dark Redwood	757 Antique Gold (SRI 41)	757 Old Gold	338 Buckskin (SRI 24)	338 Leather
288 Rosemary	288 Ginger (SRI 41)	755 Trail Dust	755 Driftwood (SRI 40)	385 Taupe (SRI 29)	385 Lava (SRI 23)
288 Bamboo (SRI 41)	288 Straw (SRI 48)	755 Spice (SRI 41)	755 Apricot	385 Buffalo (SRI 20)	385 Bark (SRI 16)



Loadings in four-color groupings are represented as follows:




These color chips represent shades of integral color using medium tone grey Type I, II, III Portland cement with a 4" slump. Use this chart as a guideline only. The colors may not exactly represent the final color. Shade variations of cement and aggregate, plus variations in the mix design, volume of water, addition of admixtures and other additives, finishing and sealer will have an effect on the final color. The colors shown on this color chart represent unsealed colored concrete. Use of a concrete sealer may darken the color. Therefore, we recommend that a test slab be poured and approved prior to the start of the job.



Only available from ColorSelect and QuickColor dispensers.



Caution:
908 Carbon Black can negate the amount of entrained air in the concrete mix. See back page for more information



**Not available in granular pigment